

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau




(43) International Publication Date
1 March 2001 (01.03.2001)

PCT

(10) International Publication Number
WO 01/14466 A1

- (51) International Patent Classification⁷: C08K 5/103, (74) Agents: HARDING, Charles, Thomas et al.; D. Young & Co., 21 New Fetter Lane, London EC4A 1DA (GB).
C07C 69/675, 69/732
- (21) International Application Number: PCT/IB00/01173 (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (22) International Filing Date: 9 August 2000 (09.08.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
9919683.4 19 August 1999 (19.08.1999) GB
60/167,923 29 November 1999 (29.11.1999) US
- (71) Applicant (*for all designated States except US*):
DANISCO A/S [DK/DK]; Langebrogade 1, P.O. Box 17,
DK-1001 Copenhagen K (DK).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): NIELSEN, Bjarne
[DK/DK]; Lundgardevej 26, DK-8732 Hovedgard (DK).
SPARSO, Flemming, Vang [DK/DK]; P.B. Lunds Vej 37,
DK-8660 Skanderborg (DK). KRISTIANSEN, Jorgen,
Kirk [DK/DK]; Vestergade 24.2, DK-7100 Vejle (DK).
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— With international search report.
— Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: COMPOSITION



(57) Abstract: There is provided composition comprising i) a thermoplastic polymer; ii) a compound having formula (I) wherein R₁, R₂ and R₃ are independently selected from an acyl group or a hydrogen atom, wherein at least one of R₁, R₂ and R₃ is an acyl group (a short acyl group) having from 2 to 6 carbon atoms, wherein at least one of R₁, R₂ and R₃ is a branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and a hydrophilic branch group.

WO 01/14466 A1


COMPOSITION

The present invention relates to a composition. In particular, the present invention relates to a composition comprising a thermoplastic polymer and a compound which acts
 5 as a plasticiser.

The manufacturing properties of thermoplastic polymers, for example the extruding properties of such polymers, is often modified/enhanced by the addition of plasticisers thereto. As acknowledged in the prior art, such as in US-A-4426477, there is a tendency
 10 toward avoiding the commonly used plasticisers such as dioctyl adipate (DOA) and phthalate plasticisers such as dioctyl phthalate (DOP). The safety of these plasticisers has been called into question, particularly in certain applications.

US-A-4426477 discloses plasticisers based on glycerol esters. The plasticisers consist of
 15 compounds prepared by the acylation of glycerol. The compounds comprises triesters, wherein approximately two of the acyls have two carbons and the remaining one acyl has from 10 to 14 carbons. The compounds of US-A-4426477 provide a plasticising effect. However, in certain applications the plasticisers have a volatility such that they may migrate out of the thermoplastic polymer in which they are incorporated, such as PVC.

20 In a first aspect the present invention provides a composition comprising i) a thermoplastic polymer ii) a compound having the formula




wherein R_1 , R_2 and R_3 are independently selected from an acyl group or a hydrogen atom, wherein at least one of R_1 , R_2 and R_3 is an acyl group (a short acyl group) having
 25 from 2 to 6 carbon atoms, wherein at least one of R_1 , R_2 and R_3 is a branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and a hydrophilic branch group.

30 Preferably two of R_1 , R_2 and R_3 are short acyl groups as described above and the other of


2

R_1 , R_2 and R_3 is a long acyl group as described above. In this aspect, the compound may be of the formula



- 5 Preferably the hydrophilic branch group is a group selected from acyl and derivatives thereof. Preferred derivatives include groups of the formula -O-acyl.

Preferably the hydrophilic branch group is a group of the formula




- 10 wherein p is from 0 to 4 or 0 to 3.

In a preferred aspect of the present invention the chain of the long acyl group consists of a saturated chain having 14 to 20 carbon atoms. In a more preferred aspect, the chain of the long acyl group consists of a saturated chain having 16 to 20 carbon atoms.

15

Preferably the long acyl group is of the formula




wherein n is from 10 to 20 and m is $2n$, and wherein p is from 0 to 4 or 0 to 3.

- 20 Preferably n is from 16 to 20, more preferably from 16 to 18, yet more preferably 17.

Preferably the group C_nH_m is a straight chain hydrocarbon group.

In a highly preferred aspect the long acyl group is a group of the formula



25


3

wherein x is from 7 to 10, preferably x is 10, and y is 2x, and wherein p is from 0 to 4 or 0 to 3, preferably p is 0.


Preferably the group C_xH_y is a straight chain hydrocarbon group.

5


In a highly preferred aspect the long acyl group is a group of the formula




10 In a preferred aspect of the present invention the short acyl group is an acyl group having from 2 to 5 carbon atoms. In a more preferred aspect, the short acyl group is an acyl group having 2 carbon atoms. The short acyl group is preferably of the formula



15 Preferably the short acyl group and the hydrophilic branch group contain the same number of carbon atoms. In a highly preferred aspect the hydrophilic branch group is a group of the formula



and the short acyl group is of the formula



20 wherein p = q and is from 0 to 4 or 0 to 3.

In certain aspects, it is desirable for the short acyl groups to be present in a maximum amount with respect to the total amount glycerol and esters thereof present in the composition. Preferably the short acyl group is present in an amount, on average, of no
25 greater than 2 moles per mole of glycerol and esters thereof present in the composition.

In certain aspects, it is desirable for the long acyl groups to be present in a minimum amount with respect to the total amount glycerol and esters thereof present in the


composition. Preferably the long acyl group is present in an amount, on average, of at least 0.4 moles, preferably from 0.9 to 2 moles, more preferably from 0.9 to 1 moles per mole of glycerol and esters thereof present in the composition.

- 5 It may also be preferred for the majority of the glycerol present in the composition to be fully acylated. Accordingly, in a preferred aspect the total amount of acyl groups is, on average, 2.7 to 3.0 moles per mole of glycerol and esters thereof

10 The compound of the present invention may be prepared by interesterification between glycerol and one or more oils, including natural oils and hardened natural oils followed by acylation. Thus, the compound of the present invention may be the product of a two part process comprising (i) an interesterification between glycerol and an oil selected from castor oil, including hardened castor oil, unhardened castor oil and mixtures thereof, and (ii) acylation.

15


Thus in a further aspect the present invention provides a process for the preparation of a compound having the formula



20 wherein R_1 , R_2 and R_3 are independently selected from an acyl group or a hydrogen atom; wherein at least one of R_1 , R_2 and R_3 is an acyl group (a short acyl group) having from 2 to 6 carbon atoms or from 2 to 5 carbons; wherein at least one of R_1 , R_2 and R_3 is a branched chain acyl group (a long acyl group) consisting of a chain having 10 to 20 carbon atoms and a hydrophilic branch group;

the process comprising the steps of:

- 25 (i) interesterification between glycerol and triglyceride compound having the formula



wherein each of R_1 , R_2 and R_3 is a fatty acid group consisting of a chain having 10 to 20

carbon atoms, to provide a composition comprising glycerol, monoglyceride, diglyceride and/or triglyceride;

(ii) optionally isolating the monoglyceride and/or diglyceride from the composition;

(iii) acylating the monoglyceride and/or diglyceride or the composition containing the same.

In the process of the present invention the chain having 10 to 20 carbon may be saturated or unsaturated.

The process of the present invention may utilise, for example, castor oil or hardened castor oil. The compound of the present invention may be prepared from hardened castor oil. A typical fatty acid profile of castor oil and hardened castor oil is given below.

Castor Oil		Hardened Castor Oil	
Fatty Acid	Content [%]	Fatty Acid	Content [%]
Palmitic (C16)	1.0	Palmitic (C16)	1.3
Stearic (C18)	1.1	Stearic (C18)	9.3
Oleic (C18:1)	3.8	Oleic (C18:1)	0.9
Linoleic (C18:2)	4.4	Linoleic (C18:2)	0.2
Linolenic (C18:3)	0.5	Arachidic (C20)	0.7
Gadoleic (C20:1)	0.5	Ricinoleic hard (C18-OH)	84.9
Ricinoleic (C18:1-OH)	87.4		


The nomenclature in parenthesis is Cxx:y where xx is the fatty acid carbon number and y indicates number of double bonds. Ricinoleic acid, hard (also known as 12-hydroxy stearic acid) has a hydroxyl group (OH) on the 12th carbon.

In this aspect the product based on the castor oil, or indeed a product based on another oil, may be synthesised as follows. These synthetic routes are given by way of example only. Other routes would be appreciated by a person skilled in the art

ROUTE 1

Castor oil and glycerol are reacted to produce an equilibrium mixture of different

glycerol esters. This mixture can be distilled and subsequently acetylated to provide the desired end products. This route is illustrated below.



The second step comprising the removal of the glycerol followed by distillation is optional. In other word the mixture of glycerol, glycerol monoester, glycerol diester, and glycerol triester may directly acetylated with acetic anhydride to form a mixture of acetylated products. The acetylated monoglyceride or the mixture of acetylated products may have a yellowish colour. The yellowish product may be distilled. The distilled product is clear.

Depending on the ratio between castor oil and glycerol and depending on the reaction conditions, the described process provides different glycerol ester mixtures. The glycerol monoester is typically 45-65% and may be up to 65%. This is achieved in a typical reaction mixture. Such a composition may then, optionally, be further processed to provide a product having a higher purity, for example a monoester content of above 90%.


Typical further processing would involve the removal of glycerol and the subsequent distillation of the resulting mixture. By means of this further processing an end product with a typical glycerol monoester content above 90% may be provided. The fatty acid profile of the end product would reflect the fatty acid profile of the castor oil starting material. This process, namely the production of a glycerol monoester, is described in Bailey's Industrial Oil & Fat Products, vol. 4, Fifth ed. P.572 ff

The glycerol monoester may then be reacted with an excess of acetic anhydride resulting

in acetic acid being esterified with the glycerol ester. Any excess of acetic anhydride is removed from the reaction mixture. The end product is a fully acetylated monoglyceride based on castor oil (which may be hardened or unhardened castor oil).

5 ROUTE 2

Route 2 provides a further manner in which acetylated monoglycerides based on, for example, hardened and unhardened castor oil may be synthesised. An acetylated monoglyceride may be produced by the reaction of castor oil with acetic anhydride to
10 provide an acetylated castor oil. The acetylated castor oil is then reacted with triacetin to produce acetylated monoglycerides based on hardened and unhardened castor oil. This process is illustrated below.






Castor oil is reacted with acetic anhydride to produce an acetylated castor oil. The
15 degree of acetylation may be defined as castor oil containing at least one acetic acid group and up to the average of three acetic acid groups per mole of castor oil. The acetylated castor oil is then reacted with triacetin to produce a reaction mixture of mainly acetylated glycerolesters with a fatty acid profile similar to that of the castor oil starting material. This mixture is purified by distillation. The end product is an acetylated
20 monoglyceride based on hardened or unhardened castor oil.

A process for obtaining acetylated glycerol esters from the reaction of a triglyceride and triacetin is described in the Danish Patent No. 93 786. The synthesis of acetylated monoglycerides based on castor oil from the starting materials acetylated castor oil and
25 triacetin is analogous to that process.

In a highly preferred aspect the compound of the present invention is selected from


compounds of the formula




These preferred compounds may be prepared and are preferably prepared in accordance with Route 1 or Route 2 above.

5


The above compounds are specific compounds which may be provided by the present invention. In a broad aspect, the present invention further provides a compound of the formula



10 wherein two of R_4 , R_5 , and R_6 are of the formula



wherein for each of the two of R_4 , R_5 , and R_6 q is independently selected from 0 to 4 or from 0 to 3; and the other of R_4 , R_5 , and R_6 is a branched group of the formula




15 wherein n is from 10 to 20 and m is $2n$, and wherein p is from 0 to 4 or from 0 to 3.

Preferably q is 0. More preferably for both of the two of R_4 , R_5 , and R_6 q is 0.

Preferably n is from 16 to 20, more preferably from 16 to 18, yet more preferably 17.

Preferably the group C_nH_m is a straight chain hydrocarbon group.

In a preferred aspect the branched group is a group of the formula



wherein x is from 7 to 10, preferably x is 10, and y is $2x$, and wherein p is from 0 to 4 or from 0 to 3, preferably p is 0.

Preferably the group C_xH_y is a straight chain hydrocarbon group.

The compounds provided by the present invention may be incorporated in a composition comprising a thermoplastic polymer. Accordingly in a further aspect the present invention provides a composition comprising a compound as defined above and a thermoplastic polymer.


The thermoplastic polymer of the compositions of the present invention may be or comprise a vinyl chloride polymer or a vinyl chloride copolymer selected from vinyl chloride/vinyl acetate copolymer, vinyl chloride/vinylidene chloride copolymer, vinyl chloride/ethylene copolymer and a copolymer prepared by grafting vinyl chloride onto ethylene/vinyl acetate copolymer, or a mixture thereof.

In a preferred aspect the thermoplastic polymer is or comprises a polymer blend of a thermoplastic polymer, preferably a thermoplastic polymer as defined above, and a second polymer. Preferably, the second polymer is a methacryl polymer or an acrylonitrile-butadiene-styrene polymer.


The compositions of the present invention may be formulated in any manner to provide the required plasticising properties of the compound. In a particular aspect the composition of the present invention comprises the compound in an amount of 1 to 100 parts by weight per 100 parts by weight of the thermoplastic polymer.

PROCESS OF INVENTION

- As disclosed above the present invention provides a process for the preparation of a
 5 compound having the formula



- wherein R_1 , R_2 and R_3 are independently selected from an acyl group or a hydrogen
 atom, wherein at least one of R_1 , R_2 and R_3 is an acyl group (a short acyl group) having
 from 2 to 5 or from 2 to 6 carbon atoms, wherein at least one of R_1 , R_2 and R_3 is a
 10 branched chain acyl group (a long acyl group) consisting of a chain having 10 to 20
 carbon atoms and a hydrophilic branch group, the process comprising the steps of: (i)
 interesterification between glycerol and triglyceride compound having the formula




- wherein each of R_1 , R_2 and R_3 is a fatty acid group consisting of a chain having 10 to 20
 15 carbon atoms, to provide a composition comprising glycerol, monoglyceride, diglyceride
 and/or triglyceride; (ii) optionally isolating the monoglyceride and/or diglyceride from
 the composition; (iii) acylating the monoglyceride and/or diglyceride or the composition
 containing the same.

- 20 In the process of the present invention the chain having 10 to 20 carbon atoms may be
 saturated or unsaturated.

In preferred aspects the compound prepared by the process is a compound of the present
 invention as described herein. In a broader aspects


- 25 • the long acyl group is of the formula



11


wherein n is from 10 to 20 and m is selected from 2n, 2n-2, 2n-4 and 2n-6, and wherein p is from 0 to 4 or from 0 to 3.

- Preferably m is 2n or 2n-2.
- Preferably the group C_nH_m is a straight chain hydrocarbon group. The straight chain hydrocarbon group may be saturated or unsaturated. The straight chain hydrocarbon group may contain a single $-C=C-$ bond.
- the long acyl group is a group of the formula




wherein x is from 7 to 10, preferably x is 10, and y is $2x-2$, and wherein p is from 0 to 4 or from 0 to 3, preferably p is 0.


- Preferably the group C_xH_y is a straight chain hydrocarbon group. The straight chain hydrocarbon group may be saturated or unsaturated. The straight chain hydrocarbon group may contain a single $-C=C-$ bond.
- the long acyl group is a group of the formula




- the compound is of the formula



- the compound is of the formula




wherein two of R_4 , R_5 , and R_6 are of the formula



wherein for each of the two of R_4 , R_5 , and R_6 q is independently selected from 0 to 4


or from 0 to 3

and the other of R_4 , R_5 , and R_6 is a branched group of the formula



wherein n is from 10 to 20 and m is selected from $2n$, $2n-2$, $2n-4$ and $2n-6$, and
 5 wherein p is from 0 to 4 or from 0 to 3. Preferably q is 0. More preferably for both of the two of R_4 , R_5 , and R_6 q is 0. Preferably n is from 16 to 20, more preferably from 16 to 18, yet more preferably 17. Preferably m is $2n-2$.

- the branched group is a group of the formula



10 wherein x is from 7 to 10, preferably x is 10, and y is $2x-2$, and wherein p is from 0 to 4 or from 0 to 3, preferably p is 0.

The invention will now be described in further detail with in the following Examples.

15


EXAMPLES

PLASTICISERS EVALUATED


20 Six plasticisers were evaluated. These were:

1. dioctyl phthalate (DOP) – a conventional phthalate based plasticiser. DOP is by far the most widely used plasticiser for PVC. DOP is available from Monsanto Europe, Belgium
2. Diisononyl phthalate (DINP) – a conventional phthalate based plasticiser from
 25 Monsanto Europe, Belgium
3. Compound A – a compound having the structure


13




4. Compound B – a compound having the structure



5. Compound C – a compound having the structure



6. Compound D – a compound having the structure



DOP, DINP and compound A are comparative compounds not in accordance with the compound/composition of the present invention. Compounds B, C and D are compounds containing saturated long chains in accordance with the present invention.

SYNTHESIS

The compounds were prepared as follows.

Synthesis of Compound A (Process of the Invention)

100 gram of castor oil, 30 gram of glycerol and 0.3 gram of 50% sodium hydroxide is heated to 250°C and reacted for 60 minutes. The sodium hydroxide is neutralised with 0.5 gram of 85% phosphoric acid. The glycerol is removed by water vapour distillation
5 at 140°C and 0.05 mbar. The monoglyceride is concentrated by short path distillation at 200°C and a pressure below $5 \cdot 10^{-3}$ mbar. 40 gram of monoglyceride is then reacted with 40 gram of acetic anhydride at 140°C for 60 minutes and the formed acetic acid is removed by vacuum distillation. The yield of compound A is 50 gram.

10 The synthesis provided a composition (Composition A) containing approximately 90 wt.% of a plasticiser compound A.

Synthesis of Compound B (Compound of the Invention)

15 100 gram of hydrogenated castor oil is reacted with 32 gram of acetic anhydride at 140°C for 60 minutes and the formed acetic acid is removed by vacuum distillation. 100 gram of the fully acetylated hydrogenated castor oil is reacted with 100 gram of triacetin, 0.0045 of sodium methoxide and 0.825 gram of aluminium stearate at 250°C for 60 minutes. The non reacted triacetin is removed by vacuum distillation at 135°C and 0.01
20 mbar. Compound B is concentrated by short path distillation at 200°C and a pressure below $5 \cdot 10^{-3}$ mbar. The yield of compound B is 40 gram.

The synthesis provided a composition (Composition B) containing approximately 90 wt.% of a plasticiser compound B.

25

Synthesis of Compound C (Compound and Process of the Invention)

100 gram of hydrogenated castor oil, 30 gram of glycerol and 0.3 gram of 50% sodium hydroxide is heated to 250°C and reacted for 60 minutes. The sodium hydroxide is
30 neutralised with 0.5 gram of 85% phosphoric acid. The glycerol is removed by water vapour distillation at 140°C and 0.05 mbar. The monoglyceride is concentrated by short path distillation at 200°C and a pressure below $5 \cdot 10^{-3}$ mbar. 40 gram of monoglyceride

is then reacted with 54 gram of butyric anhydride at 150°C for 90 minutes and the formed butyric acid is removed by vacuum distillation. The yield of compound C is 61 gram.

- 5 The synthesis provided a composition (Composition C) containing plasticiser compound C.

Synthesis of Compound D (Compound and Process of the Invention)

- 10 100 gram of hydrogenated castor oil, 30 gram of glycerol and 0.3 gram of 50% sodium hydroxide is heated to 250°C and reacted for 60 minutes. The sodium hydroxide is neutralised with 0.5 gram of 85% phosphoric acid. The glycerol is removed by water vapour distillation at 140°C and 0.05 mbar. The monoglyceride is concentrated by short path distillation at 200°C and a pressure below $5 \cdot 10^{-3}$ mbar. 40 gram of monoglyceride
15 is then reacted with 74 gram of hexanoic acid anhydride at 160°C for 90 minutes and the formed hexanoic acid is removed by vacuum distillation. The yield of compound D is 67 gram.

- The synthesis provided a composition (Composition D) containing plasticiser compound
20 D.

EXAMPLE 1

- Plasticiser composition B is tested for its function as a plasticiser using the following
25 formulation.

Formulation

- | | |
|-----------------------------|---------------------|
| PVC (K=70), Vestolit S7054* | 100 parts by weight |
| Ca-Zn stabilizer | 1 parts by weight |
| 30 Epoxidised soybean oil | 3 parts by weight |
| Plasticiser composition | 50 parts by weight |

* - available from Hüls AG, Germany

Test Procedure

5 A predetermined amount of plasticiser composition is added to the above formulation and the mixture kneaded at 150 to 155°C for 5 minutes between 20 cm test rollers. The rolled sheet is further pressed at 160°C and 150 kg/cm² using a compression molding machine to form a 1-mm thick sheet.

The test procedure demonstrates that Composition B provides a plasticising effect.

10

EXAMPLE 2

Plasticiser composition B and the four plasticisers of Example 2 of US 4426477 are tested for their function as a plasticiser using a PVC paste resin formulation.

15

Formulation

PVC (K=78), Vestolit P1348K*

100 parts by weight

Ca-Zn liquid stabilizer

3 parts by weight

Plasticiser composition

60 parts by weight

20

* - available from Hüls AG, Germany

Test Procedures

25 Bleeding Property - after deaeration the compositions are spread over a glass plate to form a 1 mm thick film. The film is allowed to gel for 15 minutes in an oven at 180°C. The resulting sheet is left to stand at room temperature for a week. The bled matter is washed off with an acetone/IPA mixture. The sheet is dried to measure its weight loss.

The test procedure demonstrates that Composition B bleeds less than each of the compositions of US 4426477.

30

EXAMPLE 3

Plasticiser composition B is evaluated by using an ethylene/vinyl chloride copolymer sheet formulation.

5 Formulation

Ethylene/vinyl copolymer (K = 55)*	100 parts by weight
Ca-Zn stabiliser	2.0 parts by weight
Methylmethacryl-butadiene-styrene resin	5.0 parts by weight
Lubricant, stearic acid monoglyceride	1.0 parts by weight
10 Polyethylene wax	0.3 parts by weight
Plasticiser composition	3.0 parts by weight

* - available from Hüls AG, Germany

15 Test Procedure

The above formulation is kneaded at 180 to 190°C for 5 minutes between 20 cm test rollers. The processability is judged at this point. Next, the rolled sheet is further pressed at 180°C and 100 kg/cm² to form a 1 mm thick sheet, and then the transparency is measured.

20

The test procedure demonstrates that Composition B provides a polymer composition having good processability and good transparency.

EXAMPLE 4

25

Plasticiser composition B is evaluated by using a PVC wrap formulation.

Formulation

PVC (K=70), Vestolit S7054	100 parts by weight
30 Epoxidised soybean oil	10 parts by weight
Ca-Zn stabiliser	2 parts by weight
Chelator	0.5 parts by weight

Antifogging agent sorbitan laurate	1.0 parts by weight
Polyoxyethylene alkyl ether	1.0 parts by weight
Plasticiser composition	35 parts by weight

5 Test Procedure

The above formulation is moulded into a wrap film by use of a 19 mm extruder and the film is subjected to tests for evaluation of properties.

Specifications of Extruder

- 10 A Brabender extrusiograph Type 19/25 D
Screw diameter 19 mm, L/D=25, die 25 mm wide die
Screw compression ration 2:1

Extrusion Conditions

- | | |
|---------------------------|----------|
| Cylinder head temperature | 195°C |
| 15 Die temperature | 205°C |
| Screw speed | 35 rpm |
| Take-off speed | 12 m/min |

- The test procedure demonstrates that Composition B provides a polymer composition
20 having good processability, good transparency, bleeding and antifogging properties.

EXAMPLE 5

Each of the six compounds being evaluated were incorporated in PVC.

25

The compounds were incorporated in the PVC in the following amounts.

PVC (K=70), Solvic S 271 GC*	100 parts by weight
Plasticiser	40 parts by weight

30

* - available from Solvay & Cie, Belgium

The PVC and plasticiser compounds were mixed in a Brabender Planetary Mixer Type P 600. The mixer was operated at 88°C and 100 RPM. The procedure is in accordance with ISO/DIS 4574.

- 5 The individual compounds are compression moulded into sheets having a thickness of approximately 4 mm in accordance with ISO 293-1974. Conditions were 190°C and an applied pressure of 7.5 bar. Moulding time was set to 150 seconds.

- 10 Dumbbell test specimens were cut from the compression moulded sheets according to DIN 53457 (Dumbbell no. 4). The properties measured to evaluate the plasticiser effect are shown in the table below. Shore A was measured according to DIN 53505. All other properties were recorded in accordance with DIN 53457.

Results

Plasticiser	Youngs Modulus [Mpa]	Strain at Break [%]	Stress at Break [MPa]	Shore A (after 3 sec.)	Shore A (after 15 sec.)	SASE (100%) [Mpa]
DOP	12.04	639.3	22.20	92.5	90.0	8.46
DINP	15.04	687.4	24.08	94.0	91.5	9.31
Compound A	16.14	678.7	28.01	91.0	88.0	10.40
Compound B	12.96	733.0	24.98	91.0	88.0	9.07
Compound C	25.89	690.4	23.83	95.0	92.0	10.51
Compound D	101.20	474.8	19.89	98.0	97.0	12.88

15

The parameters typically used to describe the plasticising effect is Young's Modulus and Shore A values.

- Young's Modulus is also called the elasticity modulus and the lower the value of this parameter the better is the plasticising effect.
- 20 • Shore A is a measure of the hardness of the product. This value should in general be as low as possible.

The stress required for a 100% elongation of the test specimen (SASE, 100%) is also used to evaluate the properties of a plasticiser. A low value on this parameter indicates a
25 good plasticising effect.

The "Strain at Break" and "Stress at Break" are two additional mechanical properties

that are used to describe a plasticised PVC.

In comparison to the industry standard plasticiser DOP, Compound B provided analogous performance to DOP. Compound B provided superior performance when compared to Compound A and DINP. Compound C and D exhibited a plasticising effect but exhibited inferior performance compared to Compound B.

EXAMPLE 6

Each of the six compounds being evaluated were incorporated in PVC.

The compounds were prepared in accordance with Example 5 and incorporated in the PVC in the following amounts.

- 15 PVC (K=70), Solvic S 271 GC* 100 parts by weight
Plasticiser 60 parts by weight

* - available from Solvay & Cie, Belgium

Plasticiser	Youngs Modulus [MPa]	Strain at Break [%]	Stress at Break [MPa]	Shore A (after 3 sec.)	Shore A (after 15 sec.)	SASE (100%) [MPa]
DOP	3.87	878.4	17.71	79.0	76.5	3.81
DINP	4.46	882.0	19.15	83.5	80.0	4.31
Compound A	4.99	815.0	18.49	79.0	75.5	4.70
Compound B	4.19	868.2	18.42	80.5	78.0	3.88
Compound C	6.65	756.0	18.05	88.0	85.0	5.48
Compound D	64.43	487.5	18.23	97.0	93.5	10.73

20

Results for this formulation which contains 60 parts plasticiser shows a better plasticising effect for all products in comparison to the results obtained with the formulation of Example 5 (40 parts plasticiser).


25 As for Example 5 in comparison to industry standard DOP, Compound B provided analogous performance to DOP, in particular in respect of Young's Modulus, SASE (100%) and Shore A. Compound B provided superior performance when compared to

Compound A and DINP. Compound C and D exhibited a plasticising effect but exhibit inferior performance than Compound B.

- 5 All publications mentioned in the above specification are herein incorporated by reference. Various modifications and variations of the described methods and system of the invention will be apparent to those skilled in the art without departing from the scope and spirit of the invention. Although the invention has been described in connection with specific preferred embodiments, it should be understood that the invention as
10 claimed should not be unduly limited to such specific embodiments. Indeed, various modifications of the described modes for carrying out the invention which are obvious to those skilled in chemistry or related fields are intended to be within the scope of the following claims.

CLAIMS:


1. A composition comprising
- i) a thermoplastic polymer
- 5 ii) a compound having the formula



- wherein R_1 , R_2 and R_3 are independently selected from an acyl group or a hydrogen atom,
- wherein at least one of R_1 , R_2 and R_3 is an acyl group (a short acyl group) having from 2
- 10 to 6 carbon atoms
- wherein at least one of R_1 , R_2 and R_3 is a branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and a hydrophilic branch group.

- 15 2. A composition according to claim 1 wherein the hydrophilic branch group is an acyl group or a derivative thereof.

3. A composition according to claim 2 wherein the hydrophilic branch group is a group of the formula



20


wherein p is from 0 to 4.

4. A composition according to any one of the preceding claims wherein two of R_1 , R_2 and R_3 are the short acyl groups and wherein the other of R_1 , R_2 and R_3 is a long acyl
- 25 group.

5. A composition according to any one of the preceding claims wherein the chain of the long acyl group consists of a chain having 14 to 20 carbon atoms.


6. A composition according to claim 5 wherein the chain of the long acyl group consists of a chain having 16 to 20 carbon atoms.
7. A composition according to any one of the preceding claims wherein the short
5 acyl group is an acyl group having from 2 to 5 carbon atoms.
8. A composition according to claim 7 wherein the short acyl group is an acyl group having 2 carbon atoms.
- 10 9. A composition according to any one of the preceding claims wherein the short acyl group is present in an amount, on average, of no greater than 2 moles per mole of glycerol and esters thereof.
10. A composition according to any one of the preceding claims wherein the long
15 acyl group is present in an amount, on average, of at least 0.4 moles, preferably from 0.9 to 2 moles, more preferably from 0.9 to 1 moles per mole of glycerol and esters thereof.
11. A composition according to any one of the preceding claims wherein the total amount of the acyl groups is, on average, 2.7 to 3.0 moles per mole of glycerol and esters
20 thereof.
12. A composition according to any one of the preceding claims wherein the compound is an acetylated interesterification product of glycerol and an oil selected from castor oil, including hardened castor oil, unhardened castor oil and mixtures thereof.
- 25 13. A composition according to any one of the preceding claims wherein the thermoplastic polymer is or comprises a vinyl chloride polymer or a vinyl chloride copolymer selected from vinyl chloride/vinyl acetate copolymer, vinyl chloride/vinylidene chloride copolymer, vinyl chloride/ethylene copolymer and a
30 copolymer prepared by grafting vinyl chloride onto ethylene/vinyl acetate copolymer, and mixtures thereof.

14. A composition according to any one of the preceding claims wherein the thermoplastic polymer is or comprises a polymer blend of a thermoplastic polymer and a second polymer.
15. A composition according to claim 14, wherein the second polymer is a methacryl polymer or an acrylonitrile-butadiene-styrene polymer.
16. A composition according to any one of the preceding claims wherein the composition comprises the compound in an amount of 1 to 100 parts by weight per 100 parts by weight of the thermoplastic polymer.
17. A composition according to any one of the preceding claims wherein the compound has the formula




15

18. A composition according to any one of claims 1 to 16 wherein the compound has the formula




19. A composition according to any one of claims 1 to 16 wherein the compound has the formula


25




20. A compound of the formula



5 wherein two of R_4 , R_5 , and R_6 are of the formula



wherein for each of the two of R_4 , R_5 , and R_6 q is independently selected from 0 to 3 and the other of R_4 , R_5 , and R_6 is a branched group of the formula



10 wherein n is from 10 to 20 and m is $2n$, and wherein p is from 0 to 4.


21. A compound according to claim 20 wherein p is from 0 to 3.

22. A compound according to claim 20 or 21 wherein q is 0.

15

23. A compound according to claim 20, 21 or 22 wherein n is from 16 to 20, preferably from 16 to 18, more preferably 17.


24. A compound according to any of claims 20 to 23 wherein the branched group is a
20 group of the formula




wherein x is from 7 to 10 and y is $2x$, and wherein p is from 0 to 4

26


25. A compound according to claim 24 wherein p is from 0 to 3.
26. A compound according to claim 24 or 25 wherein p is 0.
- 5 27. A compound according to claim 24, 25 or 26 wherein x is 10.
28. A compound of the formula



- 10 29. A compound of the formula




30. A compound of the formula



15

31. A composition comprising a compound as defined in any one of claims 20 to 30 and a thermoplastic polymer.
32. A process for the preparation of a compound having the formula




wherein R_1 , R_2 and R_3 are independently selected from an acyl group or a hydrogen atom,

wherein at least one of R_1 , R_2 and R_3 is an acyl group (a short acyl group) having from 2 to 6 carbon atoms; wherein at least one of R_1 , R_2 and R_3 is a branched chain acyl group (a long acyl group) consisting of a chain having 10 to 20 carbon atoms and a hydrophilic branch group;

the process comprising the steps of:

(i) interesterification between glycerol and triglyceride compound having the formula



wherein each of R_1 , R_2 and R_3 is a fatty acid group consisting of a chain having 10 to 20 carbon atoms, to provide a composition comprising glycerol, monoglyceride, diglyceride and/or triglyceride;

(ii) optionally isolating the monoglyceride and/or diglyceride from the composition;

(iii) acylating the monoglyceride and/or diglyceride or the composition containing the same.

33. A process according to claim 32 wherein the compound is a compound as defined in any one of claims 20 to 30.

34. A composition according to claim 1 as substantially hereinbefore described.

35. A compound according to claim 20 as substantially hereinbefore described.

36. A process according to claim 32 as substantially hereinbefore described.

INTERNATIONAL SEARCH REPORT

Int. l. Application No
PCT/IB 00/01173

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08K5/103 C07C69/675 C07C69/732

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C08K C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JAIN ET AL: "Evaluation of plasticization of characteristics of acylated/aroylated monoricinoleins for P.V.C. resins" J. OIL TECHNOL. IND. ASS. INDIA, vol. 4, no. 1, 1972, pages 27-32, XP000980004 the whole document	1-36
X	TEUPEL, M; POLLENBERG J.: "Analyse von Rinnolsäuremonoglyceriden mittels Säulenchromatographie und Kernresonanzspektroskopie" TENSIDE, no. 9/10, 1968, pages 275-278, XP002158355 page 276 -/-	20-28

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

26 January 2001

Date of mailing of the international search report

14/02/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Friederich, P

INTERNATIONAL SEARCH REPORT

Int. l. Application No

PCT/IB 00/01173

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	CH 512 546 A (MONSANTO CO) 15 September 1971 (1971-09-15) claims; examples	1-19
A	WO 92 00349 A (MONSANTO CO) 9 January 1992 (1992-01-09) claims; examples	1-19

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IB 00/01173

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
CH 512546	A	15-09-1971	BE 674640 A	30-06-1966
			CH 476790 A	15-08-1969
			DE 1595029 A	26-03-1970
			DE 1769472 A	12-08-1971
			FR 1462671 A	01-03-1967
			GB 1139646 A	
			GB 1164750 A	17-09-1969
			IL 24872 A	12-11-1969
			LU 50165 A	29-06-1966
			NL 131852 C	
			NL 6517191 A	04-07-1966
			US 3388104 A	11-06-1968
WO 9200349	A	09-01-1992	AU 8239191 A	23-01-1992
			MX 9100041 A	28-02-1992

THIS PAGE BLANK (USPTO)